

Danchem SS Composite Hose



BS EN 13765:2018 Type 3

| Bore Diameter | | Max. Working Pressure | | Bend Radius | | Weight |
|---------------|-----|-----------------------|-----|-------------|-----|--------|
| INS | MM | BARS | PSI | INS | MM | KG/M |
| 1 | 25 | 14 | 200 | 4.0 | 100 | 0.8 |
| 1.5 | 38 | 14 | 200 | 5.5 | 140 | 1.2 |
| 2 | 50 | 14 | 200 | 7.0 | 180 | 1.9 |
| 2.5 | 65 | 14 | 200 | 8.0 | 205 | 2.5 |
| 3 | 75 | 14 | 200 | 11.0 | 280 | 3.0 |
| 4 | 100 | 14 | 200 | 15.5 | 395 | 5.2 |

CONSTRUCTION:

1. Inner Wire Helix: 316 Stainless Steel High Tensile Strength Wire
2. Lining: Polypropylene
3. Sealing Film: Polypropylene/Polyester
4. Reinforcements: Polypropylene
5. Cover: PVC Coated Polyester Cloth
6. Outer Wire Helix: 316 Stainless Steel High Tensile Strength Wire

SAFETY FACTOR:

4:1

MAX VACUUM:

This website uses cookies. By continuing to use this website, you consent to our use of these cookies.

Ok

0.9 BAR

TEMPERATURE RANGE:

-30°C to +100°C

N.B. It is important to advise Dantec of the full working parameters when ordering Composite Hoses (medium, working temperature and working pressure). Working pressure rating stated above is based on transferring product at ambient temperatures (21°C/70°F). Elevated temperatures and end fitting ratings can severely reduce the working pressure of a hose assembly. Please consult Dantec technical sales with your requirements.