

## **Danoil 3AA Composite Hose**



## BS EN 13765:2018 Type 1

Bore Diameter		Max. Working Pressure		Bend Radius		Weight
INS	MM	BARS	PSI	INS	MM	KG/M
3	75	7	100	8.0	205	1.5
4	100	7	100	10.5	265	1.9

## CONSTRUCTION:

1. Inner Wire Helix: Aluminium Wire

2. Lining: Polypropylene

3. Sealing Film: Polypropylene

4. Reinforcements: Polypropylene

5. Cover: PVC Coated Polyester Cloth

6. Outer Wire Helix: Aluminium Wire

|--|

4:1

MAX VACUUM:

0.9 BAR

**TEMPERATURE RANGE:** 

-30°C to +100°C

This website uses cookies. By continuing to use this website, you consent to our use of these cookies.

N.B. It is important to advise Dantec of the full working parameters when ordering Composite Hoses (medium, working temperature and working pressure). Working pressure rating stated above is based on transferring product at ambient temperatures (21°C/70°F). Elevated temperatures and end fitting ratings can severely reduce the working pressure of a hose assembly. Please consult Dantec technical sales with your requirements.